



DuraForm® ProX EX BLK

Strong, tough nylon 11 based plastic handles the rigors of repeated abuse for long-term use in harsh environments

General Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Sintered Part Density @ 23 °C	ASTM D792	1.02 g/cc	0.037 lb/in³
Moisture Absorption @ 23 °C	ASTM D570	0.08 %	0.080 %

Mechanical Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength, Ultimate (MPa psi)	ASTM D638	43	6210
Tensile Modulus (MPa ksi)	ASTM D638	1570	227
Elongation at Break % at 5mm/min (%) at 50mm/min (%)	ASTM D638	60 27	60 27
Flexural Strength, Ultimate (MPa psi)	ASTM D790	51	7430
Flexural Modulus (MPa ksi)	ASTM D790	1360	197
Hardeness, Shore D	ASTM D2240	76	76
Impact Strength (J/m ft-lb/in) Notched Izod Unnotched Izod	ASTM D256	75 3336	1.4 63

Features

- Outstanding durability for long-life
- Excellent impact resistance
- Fatigue resistant for applications like hinges requiring hundreds of open-close cycles
- Fuel and oil resistance make it perfect for automotive applications
- Uniform black coloring resists fading or staining
- Derived from sustainable non-petrochemical based plastics

Benefits

- Complex end-use parts can be economically manufactured without the expense of tooling
- Parts have toughness required to replace injection molded ABS and polypropylene
- Functional parts can be tested in real life environments such as crash tests or other stress simulations
- No painting required for a deep black color that doesn't fade or chip

Applications

- Housing and enclosures
- Vehicle dashboards and grilles
- Automotive bumpers
- Snap-fits, living hinges and connector type parts
- Short production consumer goods/sporting equipment
- Complex designs, especially custom ductwork
- Exhaust and duct systems for aerospace and automotive uses
- Impellers

The parts used to generate the above data were generated by building parts using 80% virgin powder using default parameters on a ProX® SLS 500 printer.



DuraForm® ProX® EX BLK

Strong, tough nylon 11 based plastic handles the rigors of repeated abuse for long-term use in harsh environments

Thermal Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Heat Deflection Temperature @ 0.45 MPa @ 1.82 MPa	D648	193 °C 57 °C	379 °F 134 °F
Coefficient of Thermal Expansion (0-145 °C) (µm/m-°C µin/in-°F)	E831	168	94
Specific Heat Capacity @ 23 °C (J/g - °C BTU/lb - °F)	E1269	1.77	0.42
Thermal Conductivity (W/m-K in/hr-ft²- °F)	E1530	0.25	1.73
Flammability	UL 94	HB	HB

Electrical Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Volume Resistivity (ohm - cm)	ASTM D257	1.09×10 ¹⁷	4.29×10 ¹⁶
Surface Resistivity (ohm)	ASTM D257	2.53×10 ¹²	2.53×10 ¹²
Dissipation Factor, 1 KHz	ASTM D150	0.051	0.051
Dielectric Constant, 1 KHz	ASTM D150	2.82	2.82
Dielectric Strength (kV/mm kV/mil)	ASTM D149	17	428



www.3dsystems.com

The parts used to generate the above data were generated by building parts using 80% virgin powder using default parameters on a ProX® SLS 500 printer.

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2017 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, ProX and DuraForm are registered trademarks and the 3D Systems logo is a trademark of 3D Systems, Inc.